


FORM PTO 1390 (REV 10-95)		U.S. DEPARTMENT OF COMMERCE PATENT AND TRADEMARK OFFICE	ATTORNEY'S DOCKET NUMBER <b>MERCK 2341</b>
<b>TRANSMITTAL LETTER TO THE UNITED STATES DESIGNATED/ELECTED OFFICE (DO/EO/US) CONCERNING A FILING UNDER 35 U.S.C. §371</b>			U.S. APPLICATION NO. (If known, see 37 CFR §1.5) <b>10/031787</b>
INTERNATIONAL APPLICATION NO. <b>PCT/EP00/06314</b>	INTERNATIONAL FILING DATE <b>5 JULY 2000</b>	PRIORITY DATE CLAIMED <b>28 JULY 1999</b>	
TITLE OF INVENTION <b>ETCHING SOLUTION, CONTAINING HYDROFLUORIC ACID</b>			
APPLICANT(S) FOR DO/EO/US <b>ZIELINSKI, Claudia, et al.</b>			
<b>Applicant herewith submits to the United States Designated/Elected Office (DO/EO/US) the following items and other information:</b>			
1. <input checked="" type="checkbox"/> This is a <b>FIRST</b> submission of items concerning a filing under 35 U.S.C. §371 2. <input type="checkbox"/> This is a <b>SECOND</b> or <b>SUBSEQUENT</b> submission of items concerning a filing under 35 U.S.C. §371. 3. <input type="checkbox"/> This express request to begin national examination procedures (35 U.S.C. §371(f)) at any time rather than delay examination until the expiration of the applicable time limit set in 35 U.S.C. §371(b) and PCT Articles 22 and 39(1) 4. <input checked="" type="checkbox"/> A proper Demand for International Preliminary Examination was made by the 19 <sup>th</sup> month from the earliest claimed priority date 5. <input checked="" type="checkbox"/> A copy of the International Application as filed (35 U.S.C. §371(c)(2)) a. <input type="checkbox"/> is transmitted herewith (required only if not transmitted by the International Bureau) b. <input checked="" type="checkbox"/> has been transmitted by the International Bureau. c. <input type="checkbox"/> is not required, as the application was filed in the United States Receiving Office (RO/US) 6. <input checked="" type="checkbox"/> A translation of the International Application into English (35 U.S.C. §371(c)(2)). 7. <input checked="" type="checkbox"/> Amendments to the claims of the International Application under PCT Article 19 (35 U.S.C. §371(c)(3)) a. <input type="checkbox"/> are transmitted herewith (required only if not transmitted by the International Bureau). b. <input type="checkbox"/> have been transmitted by the International Bureau c. <input type="checkbox"/> have not been made; however, the time limit for making such amendments has NOT expired. d. <input checked="" type="checkbox"/> have not been made and will not be made. 8. <input type="checkbox"/> A translation of the amendments to the claims under PCT Article 19 (35 U.S.C. §371(c)(3)). 9. <input type="checkbox"/> An oath or declaration of the inventor(s) (35 U.S.C. §371(c)(4)). 10. <input type="checkbox"/> A translation of the annexes to the International Preliminary Examination Report under PCT Article 36 (35 U.S.C. §371(c)(5)) <b>Items 11. to 16. below concern document(s) or information included:</b> 11. <input type="checkbox"/> An Information Disclosure Statement under 37 C.F.R. §§1.97 and 1.98. 12. <input type="checkbox"/> An assignment document for recording. A separate cover sheet in compliance with 37 C.F.R. §§3.28 and 3.31 is included 13. <input checked="" type="checkbox"/> A <b>FIRST</b> preliminary amendment. <input type="checkbox"/> A <b>SECOND</b> or <b>SUBSEQUENT</b> preliminary amendment. 14. <input type="checkbox"/> A substitute specification 15. <input type="checkbox"/> A change of power of attorney and/or address letter 16. <input type="checkbox"/> Other items or information:			

U.S. APPLICATION NO. (if known, see 37 CFR §1.2) <div style="font-size: 24pt; font-weight: bold; text-align: center;">10/031787</div>		INTERNATIONAL APPLICATION NO. PCT/EP00/06314		ATTORNEY'S DOCKET NUMBER MERCK 2341	
17. <input checked="" type="checkbox"/> The following fees are submitted: <b>BASIC NATIONAL FEE ( 37 CFR §1.492 (a) (1)-(5)):</b> Search Report has been prepared by the EPO or JPO..... \$890.00 International preliminary examination fee paid to USPTO (37 CFR §1.482)..... \$710.00 No international preliminary examination fee paid to USPTO (37 CFR §1.482) but international search fee paid to USPTO (37 CFR §1.445(a)(2))..... \$740.00 Neither international preliminary examination fee (37 CFR §1.482) nor international search fee (37 CFR §1.445(a)(2)) paid to USPTO..... \$1040.00 International preliminary examination fee paid to USPTO (37 CFR §1.482) and all claims satisfied provisions of PCT Article 33(2)-(4)..... \$100.00				<b>CALCULATIONS</b> PTO USE ONLY <div style="border: 1px solid black; height: 100px; width: 100%;"></div>	
<b>ENTER APPROPRIATE BASIC FEE AMOUNT =</b>				<b>\$890.00</b>	
Surcharge of <b>\$130.00</b> for furnishing the oath or declaration later than months from the earliest claimed priority date (37 C.F.R. §1.492(e)). <input type="checkbox"/> 20 <input type="checkbox"/> 30					
CLAIMS	NUMBER FILED	NUMBER EXTRA	RATE		
Total claims	8 - 20 =	0	x \$ 18.00		\$0.00
Independent claims	1 - 3 =	0	x \$ 84.00		\$0.00
MULTIPLE DEPENDENT CLAIM(S) (if applicable)				+ \$ 280.00	
<b>TOTAL OF ABOVE CALCULATIONS =</b>				<b>\$890.00</b>	
Reduction of 1/2 for filing by small entity, if applicable. A Verified Small Entity Statement must also be					
<b>SUBTOTAL =</b>				<b>\$890.00</b>	
Processing fee of <b>\$130.00</b> for furnishing the English translation later than months from the earliest claimed priority date (37 C.F.R. §1.492(f)). <input type="checkbox"/> 20 <input type="checkbox"/> 30					
<b>TOTAL NATIONAL FEE =</b>				<b>\$890.00</b>	
Fee for recording the enclosed assignment (37 C.F.R. §1.21(h)). The assignment must be accompanied by an appropriate cover sheet (37 C.F.R. §§3.28, 3.31). \$40.00 per property.					
<b>TOTAL FEES ENCLOSED =</b>				<b>\$890.00</b>	
				Amount to be refunded:	
				charged:	
a. <input checked="" type="checkbox"/> A check in the amount of <u>\$890.00</u> to cover the above fees is enclosed. b. <input type="checkbox"/> Please charge my Deposit Account No. <u>13-3402</u> in the amount of \$_____ to cover the above fees. A duplicate copy of this sheet is enclosed. c. <input checked="" type="checkbox"/> The Commissioner is hereby authorized to charge any additional fees which may be required, or credit any overpayment to Deposit Account No. <u>13-3402</u> . A duplicate copy of this sheet is enclosed.					
<p><b>NOTE: Where an appropriate time limit under 37 C.F.R. §§1.494 or 1.495 has not been met, a petition to revive (37 C.F.R. §1.137(a) or (b)) must be filed and granted to restore the application to pending status.</b></p> <p>SEND ALL CORRESPONDENCE TO Customer Number 23,599</p> <div style="display: flex; justify-content: space-between; align-items: flex-end;"> <div style="text-align: center;">   <div style="font-size: 24pt; font-weight: bold;">23599</div> <div style="font-size: 10pt;">PATENT TRADEMARK OFFICE</div> </div> <div style="text-align: right;"> <div style="border-bottom: 1px solid black; width: 150px; margin-bottom: 5px;"></div> <div style="font-size: 10pt;">SIGNATURE</div> <div style="border-bottom: 1px solid black; width: 150px; margin-bottom: 5px;"></div> <div style="font-size: 10pt;">NAME</div> <div style="border-bottom: 1px solid black; width: 150px; margin-bottom: 5px;"></div> <div style="font-size: 10pt;">27,969</div> <div style="border-bottom: 1px solid black; width: 150px; margin-bottom: 5px;"></div> <div style="font-size: 10pt;">REGISTRATION NUMBER</div> </div> </div> <div style="display: flex; justify-content: space-between; margin-top: 10px;"> <div>             Filed: 25 JANUARY 2002              A/J:kmo           </div> </div>					

**IN THE UNITED STATES DESIGNATED/ELECTED OFFICE**

International Application No. : PCT/EP00/06314  
International Filing Date : 5 JULY 2000  
Priority Date(s) Claimed : 28 JULY 1999  
Applicant(s) (DO/EO/US) : ZIELINSKI, Claudia, et al.  
Title: ETCHING SOLUTION, CONTAINING HYDROFLUORIC ACID

**PRELIMINARY AMENDMENT**

Commissioner for Patents  
Washington, D.C. 20231

SIR:

Prior to calculating the national fee, and prior to examination in the National Phase of the above-identified International application, please amend as follows:

**IN THE CLAIMS:**

6. (Amended) Etching solutions according to Claim 1, comprising water in an amount of from 1 to 20% by weight.
7. (Amended) Etching solutions according to Claim 1, comprising a mixture of high-purity individual components.
8. (Amended) Use of the etching solutions according to Claim 1 for the selective etching of doped silicate layers.

REMARKS

The purpose of this Preliminary Amendment is to eliminate multiple dependent claims in order to avoid the additional fee. Applicants reserve the right to reintroduce claims to canceled combined subject matter.

Attached hereto is a marked-up version of the changes made to the claims by the current amendment. The attached pages are captioned **"Version With Markings to Show Changes Made"**.

Respectfully submitted,



\_\_\_\_\_  
Anthony J. Zelano, Reg. No. 27,969  
Attorney for Applicants  
MILLEN, WHITE, ZELANO & BRANIGAN, P.C.  
Arlington Courthouse Plaza 1  
2200 Clarendon Boulevard, Suite 1400  
Arlington, VA 22201  
Direct Dial: 703-812-5311  
Facsimile: 703-243-6410  
Email: zelano@mwzb.com

AJZ:kmo

Filed: 25 January 2002

**VERSION WITH MARKINGS TO SHOW CHANGES MADE**

Claims 6 to 8 have been amended as follows:

6. (Amended) Etching solutions according to Claims 1 to 5, comprising water in an amount of from 1 to 20% by weight.
7. (Amended) Etching solutions according to Claims 1 to 6, comprising a mixture of high-purity individual components.
8. (Amended) Use of the etching solutions according to Claims 1 to 6 for the selective etching of doped silicate layers.

Etching solution comprising hydrofluoric acid

This invention relates to etching solutions comprising hydrofluoric acid and organic solvents for use in the process for the production of integrated circuits. The etching solutions according to the invention are particularly suitable for the selective etching of doped silicate layers.

- 10 In the semiconductor industry, various types of integrated circuit are produced by the deposition of various dielectric layers. These can be, for example, deposited borosilicate glass (BSG) layers, phosphorus-silicate glass (PSG) layers, boron-phosphorus-silicate glass (BPSG) layers, oxide layers of thermal oxide or oxide layers deposited from tetraethyl orthosilicate (TEOS).

- 20 At various points of the semiconductor process, doped glass layers are usually applied to undoped glass layers. These are usually boron-doped glass (BSG) on a thermal oxide, phosphorus-doped glass (PSG) on a thermal oxide or boron-phosphorus-doped (BPSG) glass on a thermal oxide. The abovementioned layers can also be applied to a TEOS oxide.

- After these doped layers have been applied, they must be removed again in places by etching. Depending on the intended application, it may be necessary to etch BSG, PSG or BPSG layers selectively to give thermal or TEOS oxide.

- 35 Since the doped layers exhibit a surface topography, due to the underlying structures, the layer thickness to be removed is not the same in all areas of the wafer. However, in order to remove sufficient material in all areas to be etched, the etching time must be selected to be sufficiently long for even the thickest

- 2 -

layers to be etched through. Since the etching medium in this so-called over-etching time acts on the underlying thermal or TEOS oxide in the areas with an originally thinner layer of doped glass, an etching medium is necessary which etches the doped oxides at a much higher rate than the undoped oxides.

For etching in spin etcher operation, preference is given here to mixtures of concentrated  $H_2SO_4$  and 50% HF. These mixtures are already selective in respect of various layers and result essentially in a uniform quality of the etched layer.

However, our own experiments with various commercially available etching media have shown inadequate selectivity during etching. It has also been found here that although selective etching can be achieved with other mixtures, the uniformity of the etching is, however, inadequate for the processes.

The object of the present invention is therefore to provide the semiconductor industry with etching mixtures for the production of integrated circuits which, while having a high etching rate, also have significantly improved selectivity and result in uniform etching.

The object is achieved by etching solutions comprising hydrofluoric acid, an organic solvent, individually or as a mixture selected from the group consisting of ethylene glycol, propylene glycol, ethanol and glycerol, and water for the production of integrated circuits.

Hydrofluoric acid is preferably employed in an amount of 5 - 20% by weight in the etching solutions according to the invention.

- 3 -

In particular, the object is achieved by etching solutions comprising only an organic solvent selected from the group consisting of ethylene glycol, propylene glycol, ethanol and glycerol.

5

The invention also relates to etching solutions comprising, as organic solvents a mixture consisting of ethylene glycol and glycerol in a mixing ratio of from 1:10 to 10:1.

10

Etching solutions which have proven good for the purposes of the invention are those which comprise, as organic solvent, ethylene glycol and glycerol in a mixing ratio of from 1:5 to 5:1.

15

The object on which this invention is based is furthermore achieved by etching solutions comprising water in an amount of from 1 to 20% by weight.

20

For the purposes of the invention, the object of this invention is achieved by etching solutions comprising a mixture of high-purity individual components.

In particular, the invention also relates to the use of the novel etching solutions described here for the selective etching of doped silicate layers.

25

The mixtures developed here enable the selectivities and uniformity of etching to be significantly improved depending on the process for the deposition of the individual layers.

30

It is advantageous that the etching rate achieved with the solutions according to the invention for the etching of PSG layers, BSG layers and BBSG layers is a multiple higher (up to > 300) than for TEOS layers or layers of thermal oxide.

35



- 4 -

These selectivities have been observed in the case of etching in a spin etcher and during dip etching processes.

- 5 Organic solvents which can be used are ethylene glycol, propylene glycol, ethanol, isopropanol, glycerol and mixtures thereof. The etching rates which can be achieved using these solvents are dependent on the solvents used and on the mixing ratio of the individual
- 10 organic solvents with one another. The etching rate is furthermore greatly affected by the amount of hydrofluoric acid present in the solution and very particularly by the amount of water present.
- 15 The hydrofluoric acid content in the mixtures tested as successful is from 5 to 20% by weight of HF. Suitable solvents are in particular pure ethylene glycol, pure propylene glycol, pure ethanol or pure glycerol. In the case of solvent mixtures, the mixtures of glycerol and
- 20 ethylene glycol in a ratio of from 1:10 to 10:1, in particular, exhibited a very selective etching behaviour.

- Especially in the dip etching process, the etching
- 25 solutions on which the invention is based exhibit significantly more uniform etching than in the case of commercially available etching solutions.

- The following table shows some examples of the
- 30 selectivities achieved between BSG glass and thermal oxide, achieved in the dip etching process.

Table 1

No.	Organic component	Selectivity (BSG to therm. oxide)
1	Ethylene glycol	97
2	Glycerol	124
3	Ethylene glycol:glycerol = 1:1	101
4	Ethylene glycol:glycerol = 1:2	69
5	Ethylene glycol:glycerol = 2:1	76

5 A great advantage over the existing mixtures is the evenness of the surface after etching. This improved uniformity has a positive effect on the etching process since it allows the over-etching times to be significantly shortened. Pictures 1 to 3 show SEM photomicrographs of a BSG layer etched by dip etching with spin etch F as comparative solution. An undesired hole which formed in the surface during etching is very clear in photomicrograph 3.

15 Corresponding holes are not found on use of the etching solutions according to the invention.

20 Experiments with the etching solutions according to invention were carried out in a spin etcher as produced and marketed by SEZ. The solutions can, however, also be used on use of comparable apparatuses. The mode of operation of a spin etcher of this type is explained diagrammatically in Fig. 1.

25 Diagrams 1 - 6 show the wafer profile of BSG wafers after the etching operation with two mixtures which are the subject-matter of the application and with spin etch F, a comparative solution. It is clearly evident from these that the layer thickness after etching with spin etch F is significantly less uniform than after etching with the mixtures in accordance with the

- 6 -

present invention. All etching experiments were carried out using the same parameters.

- 5 In particular, the etching experiments carried out showed that an excessively high water content has an adverse effect on the selectivity of the etching. Good results are accordingly achieved at a water content of from 2 to 20% by weight. Since the water content is essentially determined by the addition of hydrofluoric acid, the strongest possible hydrofluoric acid grades
- 10 are employed for the preparation of the etching solutions. Instead of 50% hydrofluoric acid, 70% hydrofluoric acid is therefore used.
- 15 In order to illustrate the effect of the amount of water present in the etching solution, Table 2 shows how the etching rates, and thus also the selectivities, change in the ethylene glycol/HF mixture at constant HF concentration, but at different water contents.

20

Table 2

Mixture	Etching rate BSG glass	Thermal oxide
70% ethylene glycol + 15% HF + 15% H <sub>2</sub> O	3310 nm/min	48 nm/min
78.6% ethylene glycol + 15% HF + 6.4% H <sub>2</sub> O	2507 nm/min	14 nm/min

- 7 -

## PATENT CLAIMS

1. Etching solutions comprising hydrofluoric acid, an organic solvent, individually or as a mixture selected  
5 from the group consisting of ethylene glycol, propylene glycol, ethanol and glycerol, and water for the production of integrated circuits.
2. Etching solutions according to Claim 1, comprising  
10 5 - 20% by weight of hydrofluoric acid.
3. Etching solutions according to Claim 1, comprising an organic solvent selected from the group consisting of ethylene glycol, propylene glycol, ethanol and  
15 glycerol.
4. Etching solutions according to Claim 1, comprising, as organic solvent, ethylene glycol and glycerol in a mixing ratio of from 1:10 to 10:1.  
20
5. Etching solutions according to Claim 1, comprising, as organic solvent, ethylene glycol and glycerol in a mixing ratio of from 1:5 to 5:1.
- 25 6. Etching solutions according to Claims 1 to 5, comprising water in an amount of from 1 to 20% by weight.
7. Etching solutions according to Claims 1 to 6, comprising a mixture of high-purity individual  
30 components.
8. Use of the etching solutions according to Claims 1 to 6 for the selective etching of doped silicate  
35 layers.

- 8 -

**ABSTRACT**

This invention relates to etching solutions which comprise hydrofluoric acid and organic solvents for use in the process for the production of integrated circuits. The etching solutions according to the invention are particularly suitable for the selective etching of doped silicate layers.

1/4




Fig. 1

2/4

Heading = Wafer profile after etching with spin etch F  
in a spin etcher

Diagram 1

Vertical measurement values





Diagram 2

Horizontal measurement values



3/4

Wafer profile after etching with ethylene  
glycol / HF (15%) in a spin etcher

Diagram 3

Vertical measurement values





Diagram 4

Horizontal measurement values





4/4

Wafer profile after etching with ethylene  
glycol / glycerol / HF (15%) in a spin etcher

Diagram 5





Diagram 6 ,



**COMBINED DECLARATION FOR PATENT APPLICATION AND POWER OF ATTORNEY**  
(Includes Reference to PCT International Applications)

ATTORNEY'S DOCKET NUMBER

As a below named inventor, I hereby declare that

My residence, post office address and citizenship are as stated below next to my name

I believe I am the original, first and sole inventor (if only one name is listed below) or an original, first and joint inventor (if plural names are listed below) of the subject matter which is claimed and for which a patent is sought on the invention entitled

ETCHING SOLUTION COMPRISING HYDROFLUORIC ACID

the specification of which (check only one item below)

- ☐ is attached hereto
- ☐ was filed as United States application
- Serial No. \_\_\_\_\_
- on \_\_\_\_\_
- and was amended
- on \_\_\_\_\_ (if applicable)

☒ was filed as PCT international applicationNumber PCT/EP00/06314on 5 July 2000

and was amended under PCT Article 19

on \_\_\_\_\_ (if applicable)

I hereby state that I have reviewed and understand the contents of the above-identified specification, including the claims, as amended by any amendment referred to above.

I acknowledge the duty to disclose information which is material to patentability as defined in 37 CFR § 1.56, including for continuation-in-part applications, material information which became available between the filing date of the prior application and the national or PCT international filing date of the continuation-in-part application.

I hereby claim priority benefits under Title 35, United States Code, § 119 or 365 (b) of the following United States provisional application(s) and of any foreign application(s) for patent or inventor's certificate or 365(a) of any PCT international application(s) designating at least one country other than the United States of America listed below and have also identified below any foreign application(s) for patent or inventor's certificate or any PCT international application(s) designating at least one country other than the United States of America filed by me on the same subject matter having a filing date before that of the application(s) of which priority is claimed

**PRIOR U.S. PROVISIONAL AND FOREIGN/PCT APPLICATION(S) AND ANY PRIORITY CLAIMS UNDER 35 U.S.C. 119:**

COUNTRY (if PCT, indicate "PCT")	APPLICATION NUMBER	DATE OF FILING (day, month, year)	PRIORITY CLAIMED UNDER 35 USC 119
Germany	199 35 446.4	28 July 1999	<input checked="" type="checkbox"/> YES <input type="checkbox"/> NO
			<input type="checkbox"/> YES <input type="checkbox"/> NO
			<input type="checkbox"/> YES <input type="checkbox"/> NO
			<input type="checkbox"/> YES <input type="checkbox"/> NO
			<input type="checkbox"/> YES <input type="checkbox"/> NO

**POWER OF ATTORNEY.** As a named inventor, I hereby appoint I. William Millen (19,544), John L. White (17,256), Anthony J. Zelano (27,960), Alan F. J. Branigan (20,565), John R. Moses (24,484), Harry B. Shubert (32,004), Brian P. Heaney (32,542), Richard J. Traverno (30,595), John A. Soper (33,103), Richard M. Lebowitz (27,067), James E. Ruiland (37,232), Nancy Axelrod (44,014), Jennifer J. Branigan (40,921), Robert E. McCarthy, (46,044), and Csaba Henner (50,908) to prosecute this application and transact all business in the Patent and Trademark Office connected therewith.

Send Correspondence to Customer No 23599

Telephone No  
703/243-6333

Direct Telephone Calls to:



23599

PATENT TRADEMARK OFFICE



23599

PATENT TRADEMARK OFFICE

## Combined Declaration for Patent Application and Power of Attorney (Continued)

(Includes Reference to PCT International Applications)

ATTORNEY'S DOCKET NUMBER

201	FULL NAME OF INVENTOR	FAMILY NAME <u>WIEGAND</u>	FIRST GIVEN NAME <u>Claudia</u>	SECOND GIVEN NAME
	RESIDENCE & CITIZENSHIP	CITY <u>64291 Darmstadt</u> <u>DEX</u>	STATE OR FOREIGN COUNTRY <u>Alsheimweg 14</u>	COUNTRY OF CITIZENSHIP <u>Germany</u>
	POST OFFICE ADDRESS	STREET <u>Frankfurter Str. 250</u>	CITY <u>64293 Darmstadt</u>	STATE & ZIP CODE/COUNTRY <u>Germany</u>
202	FULL NAME OF INVENTOR	FAMILY NAME <u>RHEIN</u>	FIRST GIVEN NAME <u>Rudolf</u>	SECOND GIVEN NAME
	RESIDENCE & CITIZENSHIP	CITY <u>64646 Heppenheim</u> <u>DEX</u>	STATE OR FOREIGN COUNTRY <u>Niemöller Strasse 7</u>	COUNTRY OF CITIZENSHIP <u>Germany</u>
	POST OFFICE ADDRESS	STREET <u>Frankfurter Str. 250</u>	CITY <u>64293 Darmstadt</u>	STATE & ZIP CODE/COUNTRY <u>Germany</u>
203	FULL NAME OF INVENTOR	FAMILY NAME <u>TEMPEL</u>	FIRST GIVEN NAME <u>Eberhard</u>	SECOND GIVEN NAME
	RESIDENCE & CITIZENSHIP	CITY <u>64342 Seeheim-Jugenheim</u> <u>DEX</u>	STATE OR FOREIGN COUNTRY <u>Alsbacher Strasse 4</u>	COUNTRY OF CITIZENSHIP <u>Germany</u>
	POST OFFICE ADDRESS	STREET <u>Frankfurter Str. 250</u>	CITY <u>64293 Darmstadt</u>	STATE & ZIP CODE/COUNTRY <u>Germany</u>
204	FULL NAME OF INVENTOR	FAMILY NAME	FIRST GIVEN NAME	SECOND GIVEN NAME
	RESIDENCE & CITIZENSHIP	CITY	STATE OR FOREIGN COUNTRY	COUNTRY OF CITIZENSHIP
	POST OFFICE ADDRESS	STREET	CITY	STATE & ZIP CODE/COUNTRY
205	FULL NAME OF INVENTOR	FAMILY NAME	FIRST GIVEN NAME	SECOND GIVEN NAME
	RESIDENCE & CITIZENSHIP	CITY	STATE OR FOREIGN COUNTRY	COUNTRY OF CITIZENSHIP
	POST OFFICE ADDRESS	STREET	CITY	STATE & ZIP CODE/COUNTRY
206	FULL NAME OF INVENTOR	FAMILY NAME	FIRST GIVEN NAME	SECOND GIVEN NAME
	RESIDENCE & CITIZENSHIP	CITY	STATE OR FOREIGN COUNTRY	COUNTRY OF CITIZENSHIP
	POST OFFICE ADDRESS	STREET	CITY	STATE & ZIP CODE/COUNTRY
207	FULL NAME OF INVENTOR	FAMILY NAME	FIRST GIVEN NAME	SECOND GIVEN NAME
	RESIDENCE & CITIZENSHIP	CITY	STATE OR FOREIGN COUNTRY	COUNTRY OF CITIZENSHIP
	POST OFFICE ADDRESS	STREET	CITY	STATE & ZIP CODE/COUNTRY

<b>Combined Declaration for Patent Application and Power of Attorney (Continued)</b> (Includes Reference to PCT International Applications)	ATTORNEY'S DOCKET NUMBER
--	--------------------------

2 0 8	FULL NAME OF INVENTOR	FAMILY NAME	FIRST GIVEN NAME	SECOND GIVEN NAME
	RESIDENCE & CITIZENSHIP	CITY	STATE OR FOREIGN COUNTRY	COUNTRY OF CITIZENSHIP
	POST OFFICE ADDRESS	STREET	CITY	STATE & ZIP CODE/COUNTRY
2 0 9	FULL NAME OF INVENTOR	FAMILY NAME	FIRST GIVEN NAME	SECOND GIVEN NAME
	RESIDENCE & CITIZENSHIP	CITY	STATE OR FOREIGN COUNTRY	COUNTRY OF CITIZENSHIP
	POST OFFICE ADDRESS	STREET	CITY	STATE & ZIP CODE/COUNTRY
2 1 0	FULL NAME OF INVENTOR	FAMILY NAME	FIRST GIVEN NAME	SECOND GIVEN NAME
	RESIDENCE & CITIZENSHIP	CITY	STATE OR FOREIGN COUNTRY	COUNTRY OF CITIZENSHIP
	POST OFFICE ADDRESS	STREET	CITY	STATE & ZIP CODE/COUNTRY
2 1 1	FULL NAME OF INVENTOR	FAMILY NAME	FIRST GIVEN NAME	SECOND GIVEN NAME
	RESIDENCE & CITIZENSHIP	CITY	STATE OR FOREIGN COUNTRY	COUNTRY OF CITIZENSHIP
	POST OFFICE ADDRESS	STREET	CITY	STATE & ZIP CODE/COUNTRY
2 1 2	FULL NAME OF INVENTOR	FAMILY NAME	FIRST GIVEN NAME	SECOND GIVEN NAME
	RESIDENCE & CITIZENSHIP	CITY	STATE OR FOREIGN COUNTRY	COUNTRY OF CITIZENSHIP
	POST OFFICE ADDRESS	STREET	CITY	STATE & ZIP CODE/COUNTRY

I hereby declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under section 1001 of Title 18 of the United States Code, and that such willful false statements may jeopardize the validity of the application or any patent issuing thereon.

SIGNATURE OF INVENTOR 201 <i>Clara Wiegand</i>	DATE 14.05.02	SIGNATURE OF INVENTOR 207	DATE
SIGNATURE OF INVENTOR 202 <i>Wolfgang</i>	DATE 14.05.02	SIGNATURE OF INVENTOR 208	DATE
SIGNATURE OF INVENTOR 203 <i>Wolfgang</i>	DATE 14.05.02	SIGNATURE OF INVENTOR 209	DATE
SIGNATURE OF INVENTOR 204	DATE	SIGNATURE OF INVENTOR 210	DATE
SIGNATURE OF INVENTOR 205	DATE	SIGNATURE OF INVENTOR 211	DATE
SIGNATURE OF INVENTOR 206	DATE	SIGNATURE OF INVENTOR 212	DATE